



PCTFE Durchlässigkeit Gasförmige Medien

Temp. in °C	N ₂	O ₂	CO ₂	H ₂	H ₂ S	Wasserdampf
0	-	0,07	0,35	3,20	-	-
25	0,05	0,40	1,40	9,80	1,00	1,00
50	0,30	1,40	2,40	24,00	0,35	10,00
75	0,91	5,70	15,00	-	2,00	28,00
100	-	-	-	-	-	10,00